



Mineral Turpentine Thinner –Product Data Sheet

DESCRIPTION:

Mineral Turpentine is recommended for use in all alkyd topcoats and primers. Mineral Turpentine may be used in rapid drying alkyds as a retarder. It helps to keep a wet wedge when spraying, allowing for better flow, reducing dry-spray, and blushing. It is the preferred thinner for dipping or brush application.

PHYSICAL PROPERTIES

APPEARANCE : Low viscosity, clear, water white
Liquid

SPECIFIC GRAVITY : 0.82

BOILING RANGE : 146-197 C

THINNING

RECOMMENDATIONS : (Added to Alkyd coatings)

SPRAY : Up to 20% as required.
Depending on product and application

DIPPING : Up to 50% as required

PACK SIZE : 1L, 4L, 20L, 60L & 200L

Issued on Jan 2008